

INDUSTRIAL FLOOR HARDENER WITH QUARTZ AGGREGATES

DESCRIPTION

PENEFLOOR™ HARDENER is a one component, ready-to-use, dry shake industrial floor hardener. PENEFLOOR™ HARDENER consists of cement mix, various active proprietary chemicals, and quartz aggregate hardener, which has been crushed and graded to particle sizes, suitable for concrete floors and industrial troweled floors.

RECOMMENDED FOR

PENEFLOOR™ HARDENER is applied, by dry shake, on “green” concrete or concrete floor mortars, followed by mechanical or manual trowelling.

- ▶ Parking areas
- ▶ Gas stations
- ▶ Warehouse floors
- ▶ Loading and handling areas
- ▶ Feeding ramps
- ▶ Production sites

ADVANTAGES

- ▶ One component product
- ▶ Ready-to-use – No mixing errors
- ▶ Easy to apply
- ▶ Satisfactory floor hardening result
- ▶ Excellent resistant to impact and penetration
- ▶ Excellent abrasion resistance
- ▶ Surface absorption decrease
- ▶ Can be mixed with fiber reinforced mortar for improved properties
- ▶ Colour variety
- ▶ Low cost

TECHNICAL CHARACTERISTICS

Characteristics	Test Result
<i>Composition</i>	Cement-base powder
<i>Color</i>	Dark grey, red, green, etc.
<i>Chemical base</i>	High strength cement mix, graded quartz aggregates, various active proprietary chemicals
<i>Density</i>	93.6 ± 6.2 lb/ft ³ (1,5 ± 0,1 Kg/Lt)
<i>Abrasion resistance</i>	According to DIN EN 13892
<i>Hardness</i>	> 7 (Mohs Scale)
<i>Application temperature</i>	41 °F to 95 °F (5 °C to 35 °C)

DIRECTIONS FOR USE

Surface Preparation: Concrete must be screed with the appropriate means (e.g. Laser screed), using special automatic machinery, which can disperse up to 1.02 lb/ft² (5 kg/m²) of material. PENEFLOOR™ HARDENER can be dispersed manually, but in two layer application. Indicatively, 0.61 lb/ft² (3 kg/m²) on the first layer and 0.41 lb/ft² (2 kg/m²) on the second, preceded by compaction and leveling with power screed, between layers. Specifically, wait until concrete can be walked on, leaving an indentation of 1/4”-3/8” (6.5-9.5 mm). Concrete should be free of bleed water and be able to support the weight of a power trowel. Float open the surface by power trowel. Then, disperse PENEFLOOR™ HARDENER and proceed with troweling the surface. Continue with the second PENEFLOOR™ HARDENER dispersion and proceed with troweling the surface. If the surface is troweled by lath, do as mentioned above, in two layer application. Proper vibration and compaction of the concrete is essential for the result. Application time and rates are critical parameters and depend on weather conditions.

INDUSTRIAL FLOOR HARDENER WITH QUARTZ AGGREGATES

Concrete quality: The underlayment concrete must be stable with compressive strength at least 25 N/mm² (Type C 20/25 or higher quality – water/cement test) or equivalent to project specification requirements. Slump must be according to project specification requirements. Curing initial time is a crucial parameter and must be controlled, according to temperature conditions, for better levelling result, without retention time. A polyethylene film and special drainage membranes are needed at most of application procedures.

Finishing/Curing: Finishing materials and procedures are essential for an excellent result of PENEFLOOR™ HARDENER. PENEURE™ or PENESEAL FH™ systems can be used for curing, waterproofing, sealing and protection of concrete (See related Product Data Sheets).

Coverage: Indicatively, disperse PENEFLOOR™ HARDENER 0.41 – 1.02 lb/ft² (2 – 5 Kg/m²) at 1/12"-1/8" (2-3 mm) layer thickness.

SPECIAL CONSIDERATIONS

See the specifications of the concrete and the products used for the production of the product.

DO NOT dry shake material during strong wind. Temperature, relative humidity and ventilation affect application time and results. Deviation can be observed in product performance and colour uniformity, related to cement characteristics and deviations of the water quality, curing, etc.

Maintain uniform dry shake material application. Quality of the application result and "smoothed" levelled floors, are influenced in relation to the time of stress, exposure to external conditions and chemical attack.

Integral action systems, such as PENESEAL FH™, can drastically reduce these negative effects and also ensure a permanent glossy surface (See related Product Data Sheets).

Contact PENETRON HELLAS S.A. for further information, regarding your project.

PACKAGING

PENEFLOOR™ HARDENER is available in 55 lb (25 kg) bags.

STORAGE / SHELF LIFE

PENEFLOOR™ HARDENER can be stored for at least 12 months in its original packing (unopened container) at 41 – 86 °F (5 – 30 °C) in a cool, dry place. Keep away from wet areas and direct sunlight.

SAFE HANDLING INFORMATION

Contains cement, which is alkaline. May cause eyes and skin irritation. Avoid skin and eye contact. If contact is made, flush areas with lots of water and seek medical advice. Protective gloves, mask and goggles should be worn. For further information please refer to Safety Data Sheet. PENETRON HELLAS S.A. has recently updated Safety Data Sheet on the safe use of PENETRON® products. Each Safety Data Sheet contains health and safety information for the protection of your employees and your customers. KEEP OUT OF REACH OF CHILDREN.

CERTIFICATION

PENETRON HELLAS S.A.

Thrakomakedonon 50
GR 13679, Acharnes
18

12.10022.02D060318-06
EN 13813:2002

Coating and Floor Coatings
EN 13813: CT-C50-F7-A1.5

Fire behavior: A1

Emission of corrosive substances: CT

Wear resistance BOHME: A 1.5

Compressive strength: C50

Flexural strength: F7

WARRANTY – DISCLAIMER

PENETRON HELLAS S.A. warrants that its products are manufactured under certified ISO Standard procedures, are of excellent quality and shall be free from material defects and contain all components in their proper proportion. Should any of the products be proven defective, the liability to PENETRON HELLAS S.A. shall be limited to replacement of the material proven to be defective, since the standard application procedures have been met and the suitability of the product for the particular application have been proven. PENETRON HELLAS S.A. makes no warranty as to merchantability of fitness for a particular purpose. User, after contacting the distributor of the product, shall determine the suitability of the product for his intended use and assume all risks and liability in connection therewith. While every care has been taken, the information provided in this product's data sheet make no part of any contract. All recommendations, technical data and test data contained in this product's data sheet are based upon the results of control laboratory tests or in actual field tests. However, PENETRON HELLAS S.A. makes no warranty of any kind, concerning this data. In any case, this data are given in good faith based in the PENETRON HELLAS S.A. experience, till the publication of this sheet. Due to variance in storage, handling and applications of the materials, PENETRON HELLAS S.A. accepts no liability for the results obtained. It is suggested that potential users try small applications to determine the suitability of each individual product for their specific requirements. The users should always refer to the most recent edition of the product's data sheet. PENETRON HELLAS S.A. may particularly differentiate its versions of the product's data sheet compared with those of PENETRON INTERNATIONAL LTD or respective PENETRON companies worldwide. These changes are due to text formatting, different application weathering and procedures or different product names and aim at the optimal consumer information.

PENETRON HELLAS S.A.

G.E.MH. No: 07278001000

Athens Headquarters - Greece

50 - 52, Thrakomakedonon Av.

136 79 Acharnes, Greece

T: +30 210 2448250

F: +30 210 2476803

info@penetron.gr, www.penetron.gr